

RF741 Rework Flux

No-Clean Electronic Grade

Product Description

Kester RF741 Rework Flux is a high-viscosity, no-clean flux designed for electronic component rework and repair applications. RF741 has a gel-like consistency and is easily applied by syringe dispensing. RF741 can be precisely dispensed onto a specific area that needs flux. After being dispensed, RF741 stays in place until soldering occurs. Traditional problems experienced with controlling the application of low solids no-clean liquid fluxes are eliminated. RF741 has excellent performance in applications requiring a flux having good thermal stability such as surface mount component repair. RF741 is the ideal choice for QFP or BGA semi-automated rework operations. In addition, RF741 is well suited for use with through-hole repair operations where solder fountain or controlled solder reservoir is being used for selective component removal and repair. Residues that remain on surfaces after soldering are almost colorless, leaving a very cosmetically appealing repair. The residue has high electrical resistance and can be left on the assembly after soldering. Residues are compatible with all no-clean fluxes in the Kester product line. RF741 can be used in combinations with Kester no-clean cored wire solders and no-clean solder pastes, as well as no-clean liquid fluxes without any compatibility risks.

Performance Characteristics:

- Compatible with most no-clean chemistries
- Leaves bright/shiny solder joints after reflow
- Classified as ROL0 per J-STD-004
- Compliant to Bellcore GR-78

RoHS Compliance

This product meets the requirements of the Restriction of Hazardous Substances (RoHS) Directive, 2015/863 for the stated banned substances.

Physical Properties

Viscosity (typical): 180 poise

Malcom Viscometer @ 10 rpm and 25 °C

Acid Number (typical): 75.0 mg KOH/g of flux

Tested to J-STD-004, IPC-TM-650, Method 2.3.13

Reliability Properties

Copper Mirror Corrosion: Low

Tested to J-STD-004, IPC-TM-650, Method 2.3.32

Corrosion Test: Low

Tested to J-STD-004, IPC-TM-650, Method 2.6.15

Silver Chromate: Pass

Tested to J-STD-004, IPC-TM-650, Method 2.3.33

Chloride and Bromides: None Detected

Tested to J-STD-004, IPC-TM-650, Method 2.3.35

Fluorides by Spot Test: Pass

Tested to J-STD-004, IPC-TM-650, Method 2.3.35.1

Surface Insulation Resistance (SIR): Pass

Tested to J-STD-004, IPC-TM-650, Method 2.6.3.3

	Blank	RF741
Day 1	$2.5 \times 10^{10} \Omega$	$4.0 \times 10^8 \Omega$
Day 4	$1.5 \times 10^{10} \Omega$	$1.6 \times 10^9 \Omega$
Day 7	$1.4 \times 10^{10} \Omega$	$4.0 \times 10^9 \Omega$

Cleaning

RF741 is a no-clean chemistry. The residues do not need to be removed for typical applications. If residue removal is required, call Kester Technical Support.

Recycling Services

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area or [link here](#).



Storage, Handling and Shelf Life

Shelf life is 1 year from the date of manufacture when stored between 0 to 10 °C (32 to 50 °F).

Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet and warning label before using this product. Safety Data Sheets are available at this [link](#).

Contact Information

To confirm this document is the most recent version, please contact Assembly@MacDermidAlpha.com

<p>North America 109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.253.7837</p>	<p>Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400</p>	<p>Asia Pacific 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100</p>
--	--	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "R" and "TM" are registered trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.